

SQAD-6 Quality Control Notice (QCN)

Sub Code: CHPY

Charpy Impact Testing

Finished materials for which this quality statement is specified shall be Charpy V-Notch Impact tested in accordance with the latest issue of ASTM A 370. Testing shall be performed at a temperature not higher than –20 deg. F unless otherwise specified in the Exelon PO/Contract. Test results shall report the actual test temperature, the impact strength, lateral expansion, and shear area.